

Test Report

Report No.: CTT161231924ENR2

Date: Dec. 22, 2016

Page 1 of 4

Applicant: PUBLIK D.O.O.

Address: VLADIKE NIKOLAJA 469 AND CITY IS 14000 VALJEVO

The following merchandise was (were) submitted and identified by client as:

Sample Name: TRAVEL MUG

Item No.: 41.050.XX where X=(0-9) / KRIPTON | 41.043.XX where X=(0-9)/ LAVA CLEAR
| 41.049.XX where X=(0-9) /TRAVELINO PLUS

P/O No.: YF-Marko-050

Supplier: ASIA GATEWAY OVERSEAS LIMITED

Exported to: SERBIA

Buyer: PUBLIK

Sample Received Date: Dec. 16, 2016


Completed Date: Dec. 22, 2016

Test Result(s): Please refer to next page(s).

Test Requested and Conclusion(s):

No.	Test Sample	Standard and Requirement	Conclusion(s)
1	Tested materials of submitted samples	German food, Articles of Daily Use and Feed Code (LFGB), section 30&31. - Overall migration - Soluble heavy metal - Extractable components	PASS

Signed for and on Behalf of CTT



Yuhu / Lab supervisor

Consumer Testing Technology Co., Ltd.

This test report is issued by the company subject to its General Conditions of Services printed overleaf or available on request and accessible at www.cttlab.com. Attention is drawn to the limitations of liability, indemnification and jurisdictional issues defined therein. Unless otherwise stated the results shown in this report refer only to the sample(s) tested. Without prior written permission of the company, this test report cannot be reproduced, except in full. Items marked with "n" or "m" means they are not accredited by CNAS or CMA. "s" means the item of subcontractor is not accredited by CNAS or CMA.

Test Report

Report No.: CTT161231924ENR2

Date: Dec. 22, 2016

Page 2 of 4

Test Result(s):

Overall migration ^s

Method: With reference to EN1186-1:2002& EN1186-3:2002& EN1186-9:2002

Material No.	Description	Location
1	Black plastic	Cup body
2	Transparent plastic	Cup body
3	Black plastic	Lid

Material No.	Test Condition	Limit (mg/dm ²)	Result (mg/dm ²)	Conclusion
1	10% Ethanol(v/v), 100°C, 1 hours	10	<3	PASS
	3% Acetic acid(w/v), 100°C, 1 hours	10	<3	PASS
2	10% Ethanol(v/v), 100°C, 1 hours	10	<3	PASS
	3% Acetic acid(w/v), 100°C, 1 hours	10	<3	PASS
3	10% Ethanol(v/v), 100°C, 1 hours	10	<3	PASS
	3% Acetic acid(w/v), 100°C, 1 hours	10	<3	PASS

Note:

1. mg/dm² = milligram per square decimetre of surface area of material or article.
2. The requirement in accordance with the Commission Regulation (EU) No 10/2011.

This test report is issued by the company subject to its General Conditions of Services printed overleaf or available on request and accessible at www.cttlab.com. Attention is drawn to the limitations of liability, indemnification and jurisdictional issues defined therein. Unless otherwise stated the results shown in this report refer only to the sample(s) tested. Without prior written permission of the company, this test report cannot be reproduced, except in full. Items marked with "n" or "m" means they are not accredited by CNAS or CMA. "s" means the item of subcontractor is not accredited by CNAS or CMA.



Test Report

Report No.: CTT161231924ENR2

Date: Dec. 22, 2016

Page 3 of 4

Test Result(s):

Soluble heavy metal^s

Method: Preparation in 3% Acetic acid(w/v) at 100°C for 1 hours, analyzed by Inductively Coupled Plasma Atomic Emission Spectrometer (ICP-AES).

Material No.	Description	Location
1	Black plastic	Cup body
2	Transparent plastic	Cup body

Elements	Barium (Ba)	Cobalt (Co)	Copper (Cu)	Iron (Fe)	Lithium (Li)	Manganese (Mn)	Zinc (Zn)	Conclusion	
Limit (mg/kg)	1	0.05	5	48	0.6	0.6	25		
Material No.	Result (mg/kg)							Conclusion	
1	<0.1	<0.01	<1	<1	<0.1	<0.1	<1		PASS
2	<0.1	<0.01	<1	<1	<0.1	<0.1	<1		PASS

- Note:**
1. mg/kg = milligrams of the constituents released per kilogram of foodstuff.
 2. The requirement in accordance with the Commission Regulation (EU) No 10/2011.

Extractable components^s

Method: With reference to 61st Communication on testing of plastics in Bundesgesundheitsblatt, Gesundheitsforschung, Gesundheitsschutz 46 (2003) 362.

Material No.	Description	Location
4	Semi-transparent plastic	Silicone ring

Material No.	Test Condition	Limit(%)	Result(%)	Conclusion
4	10% Ethanol, Refluxing, 5 hours	0.5	<0.1	PASS

- Note:**
1. % = Percentage by weight.
 2. The requirement in accordance with BfR Recommendations on Food Contact Materials Part XV.
 3. CTT161231924ENR1 is replaced by this report.

This test report is issued by the company subject to its General Conditions of Services printed overleaf or available on request and accessible at www.cttlab.com. Attention is drawn to the limitations of liability, indemnification and jurisdictional issues defined therein. Unless otherwise stated the results shown in this report refer only to the sample(s) tested. Without prior written permission of the company, this test report cannot be reproduced, except in full. Items marked with "n" or "m" means they are not accredited by CNAS or CMA, "s" means the item of subcontractor is not accredited by CNAS or CMA.

Test Report

Report No.: CTT161231924ENR2

Date: Dec. 22, 2016

Page 4 of 4

Photo of Sample:



End of Report

This test report is issued by the company subject to its General Conditions of Services printed overleaf or available on request and accessible at www.cttlab.com. Attention is drawn to the limitations of liability, indemnification and jurisdictional issues defined therein. Unless otherwise stated the results shown in this report refer only to the sample(s) tested. Without prior written permission of the company, this test report cannot be reproduced, except in full. Items marked with "n" or "m" means they are not accredited by CNAS or CMA, "s" means the item of subcontractor is not accredited by CNAS or CMA.